

Stainless Steel Stick Electrodes

Stainless Steel Stick Electrodes

AC-DC/Sterling AP/Smootharc Plus (-16) Ideal multipurpose stainless electrodes provide smooth, uniform and finely rippled weld beads that require minimal finishing. AC-DC/Sterling AP electrodes perform well on AC or DCEP and possess outstanding out-of-position capabilities and good strike and restrike characteristics.

Sterling® (-17) A superb family of spray transfer electrodes that produces attractive, finely rippled concave weld beads. Sterling electrodes operate well in all positions, on AC or DCEP, with self-peeling slag and excellent restrike characteristics. The direct spray arc transfer is extremely stable and exhibits higher deposition rates with little spatter.

| Hobart Product | AWS Class | Smootharc Plus/ AC-DC/Sterling AP -16 | Sterling -17 |
|----------------|--------------|---|-----------------|
| 308/308H | E308 & E308H | • | • |
| 308L | E308L | • | • |
| 309 | E309 | • | • |
| 309L | E309L | • | • |
| 310 | E310 | • | ○ |
| 312 | E312 | • | ○ |
| 316/316H | E316 & E316H | • | • |
| 316L | E316L | • | • |
| 317L | E317L | • | • |
| 347 | E347 | • | • |
| 410 | E410 | • | ○ |
| 410NiMo | E410NiMo | • | ○ |
| 2209 | E2209 | • | ○ |

• Offered ○ Not Offered

NOTE: Actual certs are included in every master carton of stainless stick electrodes at no charge.

308/308H Sterling® AP 308/308H Sterling®

AWS E308-16 & E308H-160

For applications where service conditions are not severe. Intermediate layer prior to deposition of hard-facing material. Use on Types 301, 302, 304, 305, and 308 base metals. Approvals and conformances: AWS Spec A5.4, ASME SFA5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|-----------------|---------|
| Carbon | 0.06 |
| Manganese | 1.14 |
| Silicon | 0.44 |
| Chromium | 19.88 |
| Nickel..... | 9.78 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 86,000 (593 MPa) |
| Yield Strength (psi) | 65,000 (448 MPa) |
| Elongation in 2" | 45% |
| DeLong Ferrite Number | 7 |

308/308L Sterling® AP 308/308L Sterling® 308L Smootharc™ Plus

AWS 308/E308L-16

AWS 308/E308L-17

For welding Type 308L. Properties similar to Type 308 with low C to avert carbide precipitation and inhibit subsequent carbide precipitation. Approvals and conformances: AWS Spec A5.4, ASME SF5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|-----------------|---------|
| Carbon | 0.03 |
| Manganese | 1.14 |
| Silicon | 0.43 |
| Chromium | 19.68 |
| Nickel..... | 9.89 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 83,000 (572 MPa) |
| Yield Strength (psi) | 64,000 (441 MPa) |
| Elongation in 2" | 37% |
| DeLong Ferrite Number | 9 |

Stainless Steel Stick Electrodes

309 H Sterling® AP

AWS E309-16

The moisture resistant, all-position 309 (H) Sterling® AP electrode is primarily designed for welding Type 309 metal but can also be used for 18-8 clad steels or dissimilar materials if the alloy content is sufficiently high for a sound, ductile deposit. It yields a uniform weld bead that is flat to slightly convex: AWS Spec A5.4, ASME SF5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|------------|-------|
| Carbon | 0.08 |
| Chromium | 23.50 |
| Nickel | 13.00 |
| Molybdenum | 0.10 |
| Manganese | 1.05 |
| Phosphorus | 0.020 |
| Sulfur | 0.016 |
| Copper | 0.10 |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 88,000 (607 MPa) |
| Yield Strength (psi) | 67,000 (462 MPa) |
| Elongation in 2" | 37% |
| DeLong Ferrite Number | 6-15 |

309/309L Sterling® AP 309/309L Sterling® 309L Smootharc™ Plus

AWS 309/E309L-16

AWS 309/E309L-17

Low C modification of standard Type 309 analysis used for weld overlay or welding stainless to mild or low alloy steels. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|-----------|---------|
| Carbon | 0.03 |
| Manganese | 1.32 |
| Silicon | 0.41 |
| Chromium | 23.00 |
| Nickel | 13.50 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 79,000 (545 MPa) |
| Yield Strength (psi) | 64,000 (441 MPa) |
| Elongation in 2" | 41% |
| DeLong Ferrite Number | 13 |

309Mo 309MoL AC-DC

AWS E309Mo-16

AWS E309MoL-16

The addition of molybdenum to the 309 improves tensile strength and resistance. Used for 316 clad steels and joining Mo-containing steels to carbon steels: AWS Spec A5.4, ASME SF5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|------------|---------|
| Carbon | 0.03 |
| Manganese | 1.23 |
| Silicon | 0.44 |
| Chromium | 22.70 |
| Nickel | 13.60 |
| Molybdenum | 2.40 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 90,000 (621 MPa) |
| Yield Strength (psi) | 70,000 (483 MPa) |
| Elongation in 2" | 35% |
| DeLong Ferrite Number | 13 |

310 AC-DC

AWS E310-16

For welding base metal of similar composition, when the stainless base metal is of unknown composition, and for dissimilar metals. Used as a transition layer for high restrained joints of high carbon steels. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, A-9)

Typical Deposit Analysis %

| | |
|-----------|---------|
| Carbon | 0.14 |
| Manganese | 2.02 |
| Silicon | 0.46 |
| Chromium | 26.12 |
| Nickel | 21.00 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 86,000 (593 MPa) |
| Yield Strength (psi) | 63,000 (434 MPa) |
| Elongation in 2" | 40% |
| DeLong Ferrite Number | 0 |

312 AC-DC

AWS E312-16

Welding Type 312 base metals. Excellent for dissimilar metal joining due to high ferrite potentials. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, 4-8)

Typical Deposit Analysis %

| | |
|-----------|---------|
| Carbon | 0.07 |
| Manganese | 0.80 |
| Silicon | 0.40 |
| Chromium | 28.50 |
| Nickel | 9.10 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|-------------------|
| Tensile Strength (psi) | 115,000 (793 MPa) |
| Yield Strength (psi) | 95,000 (655 MPa) |
| Elongation in 2" | 25% |
| DeLong Ferrite Number | 45 |

316/316H Sterling® AP 316/316H Sterling®

AWS E316-16 & E316H-16

AWS E316-17 & E316H-17

For welding Type 316 steel. Applies where increased high temperature corrosion resistance of molybdenum-bearing steels are necessary. Low FN version. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|------------|---------|
| Carbon | 0.07 |
| Manganese | 1.63 |
| Silicon | 0.40 |
| Chromium | 18.50 |
| Nickel | 12.40 |
| Molybdenum | 2.21 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 85,000 (586 MPa) |
| Yield Strength (psi) | 68,000 (469 MPa) |
| Elongation in 2" | 45% |
| DeLong Ferrite Number | 4 |

Stainless Steel Stick Electrodes

316/316L Sterling® AP 316/316L Sterling® 316L Smootharc™ Plus

AWS 316/E316L-16

AWS 316/E316L-17

Welding Type 316L material. Properties similar to Type 316. Suited for urea environments. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|------------|---------|
| Carbon | 0.02 |
| Manganese | 1.55 |
| Silicon | 0.48 |
| Chromium | 18.20 |
| Nickel | 13.00 |
| Molybdenum | 2.27 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 82,000 (565 MPa) |
| Yield Strength (psi) | 61,000 (421 MPa) |
| Elongation in 2" | 42% |
| DeLong Ferrite Number | 2 |

317L AC-DC

AWS E317L-16

AWS E317L-17

Increased molybdenum content results in higher tensile strength, better corrosion resistance, and improved high temperature creep strength when compared with 316L. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|------------|---------|
| Carbon | 0.03 |
| Manganese | 1.21 |
| Silicon | 0.51 |
| Chromium | 18.80 |
| Nickel | 13.70 |
| Molybdenum | 3.40 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 92,000 (634 MPa) |
| Yield Strength (psi) | 69,000 (476 MPa) |
| Elongation in 2" | 35% |
| DeLong Ferrite Number | 4 |

347 AC-DC

AWS E347-16

Metal stabilized with columbium prevents carbide precipitation. Better corrosion resistance than Type 308. For welding Types 347 and 321 steels. Good corrosion resistance in steam or utility applications up to 1400°F. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|-----------|---------|
| Carbon | 0.06 |
| Manganese | 1.19 |
| Silicon | 0.46 |
| Chromium | 20.24 |
| Nickel | 10.00 |
| Columbium | 0.60 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|------------------------|------------------|
| Tensile Strength (psi) | 80,000 (552 MPa) |
| Yield Strength (psi) | 64,000 (441 MPa) |
| Elongation in 2" | 36% |
| DeLong Ferrite Number | 10 |

410 AC-DC

AWS E410-16

Air-hardening stainless for welding 12 Cr material. Requires pre and post-weld heat treatments. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|-----------|---------|
| Carbon | 0.09 |
| Manganese | 0.55 |
| Silicon | 0.29 |
| Chromium | 12.30 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|--|------------------|
| (Heat Treated for 1 hr. @ 1375°F) | |
| Tensile Strength (psi) | 80,000 (552 MPa) |
| Yield Strength (psi) | 44,000 (303 MPa) |
| Elongation in 2" | 24% |

410NiMo AC-DC

AWS E410NiMo-16

Used extensively for welding ASTM CA6NM castings as well as 410, 410S and 405 base metals. Better as-welded toughness than 410. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|------------|---------|
| Carbon | 0.02 |
| Manganese | 0.68 |
| Silicon | 0.35 |
| Chromium | 12.48 |
| Nickel | 4.30 |
| Molybdenum | 0.55 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|---|-------------------|
| (Stress Relieved for 1 hr. @ 1125°F) | |
| Tensile Strength (psi) | 134,000 (924 MPa) |
| Yield Strength (psi) | 123,000 (848 MPa) |
| Elongation in 2" | 18% |

2209 AC-DC

AWS E2209-16

Specially formulated for welding the 22 Cr-5 Ni-3 Mo (Type 2205) duplex stainless steels. The deposited duplex weld metal offers combined high strength with improved pitting and SSC resistance. Approvals and conformance: AWS Spec A5.4, ASME SFA5.4 (F-5, A-8)

Typical Deposit Analysis %

| | |
|------------|---------|
| Carbon | 0.03 |
| Manganese | 1.01 |
| Silicon | 0.38 |
| Chromium | 22.90 |
| Nickel | 10.10 |
| Molybdenum | 3.00 |
| Nitrogen | 0.093 |
| Iron | Balance |

Typical Properties and Ferrite Number of Weld Deposit as Welded

| | |
|---|-------------------|
| Tensile Strength (psi) | 115,000 (793 MPa) |
| Yield Strength (psi) | 90,000 (621 MPa) |
| Elongation in 2" | 27% |
| DeLong Ferrite Number (Extended) | 34 |
| Impact Strength, -50°F (Charpy v Notch) | 23 ft•lbf |